

GRADING OF TWO LAYERS ENGINEERED OAK FLOORING (OAK LAMELLA+EU PLYWOOD)

01 07 2023

Select grade

- healthy, cracked, not fallen out knots till 8-10 mm;
- rare occured fallen out knots till 8 mm;
- rare occurred light timber color variation, white spots;
- knots are filled;
- no sapwood.

Natur grade

- Healthy or cracked knot up to 25 mm;
- knots can be sprung, but filled;
- open knots up to 25 mm;
- rare occured micro cracks on the surface of board;
- all cracks and knots are filled;
- natural timber color variation,
- rare occurred light white spots;
- no sapwood.

Rustic A grade

- Healthy and cracked knot up to 40-45 mm
- knots can be sprung, but filled;
- open knot up to 25 mm;
- rare occured micro cracks on the surface of board;
- all cracks and knots are filled;
- rare occurred medullary ray;
- natural timber color variation, white spots;
- no sapwood.

Nature grade (Natur and Rustic A mix)

- sound not fallen out knots till 40-45 mm;
- knots can be sprung, but filled;
- fallen out knots till 25 mm;
- rare occured micro cracks on the surface of board;
- all cracks and knots are filled;
- rare occurred medullary ray;
- natural timber color variation, white spots;
- no sapwood.

Tel.: +370 37 541 303 Faks.: +370 349 79 436 El. paštas: info@staki.lt www.staki.lt



Rustic B grade

- sound not fallen out knots till 80-90 mm;
- knots can be sprung, but filled;
- permitted fallen out knots till 40 mm;
- quantity of knots are not limited;
- small cracks on the surface of board;
- all cracks and knots are filled;
- fluting of timber;
- heart boards;
- natural color variation, white spots;
- no sapwood;

Rustic B/C grade

- size and quantity of knots are not limited;
- small cracks on the surface of board;
- all cracks and knots are filled;
- fluting of timber;
- heart boards;
- natural color variation, white spots;
- no sapwood;

Copying and distributing the information without the permission of UAB "Plankmara" is strictly prohibited.

The floor manufacturer reserves the right to correct and update the information provided. The last one

information update 07.01.2023.

Tel.: +370 37 541 303 Faks.: +370 349 79 436 El. paštas: info@staki.lt www.staki.lt