


STAUF PUK-446 2c-PU Wood flooring adhesive

hard elastic 2-component polyurethane wood flooring adhesive
according to DIN 281 and DIN EN 14293

Special features:

- ▶ fast setting
- ▶ long processing time
- ▶ hard elastic, reducing tension
- ▶ very low emission



Suitable for installation of

- ▶ upright mosaic parquet lamellas, according to DIN EN 14761
- ▶ solid lamparquet products according to DIN EN 13227
- ▶ solid planks
- ▶ multiple layer wood flooring according to DIN EN 13489
- ▶ mosaic parquet according to DIN EN 13488
- ▶ wood strip flooring according to DIN EN 13226

Suitable sub floors

- ▶ calcium sulphate (flow) floor
- ▶ STAUF leveling compounds for wood flooring
- ▶ chipboards V100 (E1), OSB boards
- ▶ cement floors

Suitable primers

- ▶ STAUF VPU-155
- ▶ STAUF VEP-190

Suitable leveling compounds

- ▶ STAUF SPP-95
- ▶ STAUF SPP-90

Suitable underlays

- ▶ STAUF comfort pad
- ▶ STAUF polyester fleece
- ▶ STAUF Decoupling/stress relief board

Suitable cleaner

- ▶ STAUF Solvent cleaner
- ▶ STAUF Cleaning agent

Product properties

- ▶ not sensitive to frost
- ▶ very well spreadable
- ▶ tension reducing
- ▶ fast setting
- ▶ hard elastic

Color

- ▶ beige

Required quantities per m²

- ▶ 1000 g with STAUF notched trowel no. 3
- ▶ 1300 g with STAUF notched trowel no. 4
- ▶ 1100 g with STAUF notched trowel no. 5

Open time

- ▶ approx. 45-60 minutes at 20 °C

Accessibility

- ▶ after approx. 24 hours

Room climate at work site

- ▶ minimum 15 °C, maximum 75% rel. humidity, preferably max. 65%

Shelf-life

- ▶ minimum 12 months

Available Packaging

- ▶ 8,01 kg plastic bucket

Emicode

- ▶ EC1-R

Giscode

- ▶ RU1

Additional information for multi-component products:

Potlife

- ▶ approx. 30-45 minutes at 20 °C

Mixing ratio component A

- ▶ 9

Mixing ratio component B

- ▶ 1

Color of component B (hardener)

- ▶ brown

STAUF PUK-446

2c-PU Wood flooring adhesive



Examination of sub floor

Prior to processing, the sub floor must be checked according to the standard DIN 18356 or corresponding national standards. The sub floor shall be resistant to pressure and tension, free of cracks, must have sufficient surface strength, be permanently dry, level, clean and free of anti-adherents, sinter layers etc. In addition, porosity and grip of surface need to be checked. Also check moisture content and absorptive capacity of cement (flow) and calciumsulfate (flow) floors as well as room temperature, air humidity and sub floor temperature.

Sub floor preparation

It must be ensured that the sub floor is ready for installation by performing proper sub floor preparation, floors must be clean, have sufficient surface strength, must be level, permanently dry and free of cracks. A mechanical pre-treatment of the sub-floor (sweeping, vacuuming, mechanical brushing, sanding, milling, shot blasting) must be performed depending on type and condition of sub floor. Cracks and joints, except expansion joints and other construction joints, shall be solidly closed with STAUF casting resin and floor brackets. Cavities and indentations can be filled with a non self-leveling STAUF leveling compound. In order to improve adhesion of adhesives and leveling compounds, prime the sub floor with the appropriate primer. Always apply a primer under leveling compounds, dispersion wood flooring adhesives and under wood flooring adhesives on underfloor heating systems. If necessary, make sure sub floors are level, have sufficient absorptive capacity and grip by applying the appropriate STAUF leveling compound.

Mixing procedure of components

Add total amount of hardener no. 5 from plastic bottle to bucket containing the resin component. Mixing of the components: Mix both components thoroughly using electric drill with stir attachment or electric stirrer with disposable stir attachment until compound has reached a uniform color (stir time: minimum 2 min.). Make sure that components are well mixed on walls and bottom of bucket. Always mix complete container content in order to ensure proper mixing ratio.

Processing

Apply adhesive to sub floor using the appropriate STAUF notched trowel, avoid adhesive pooling and excessive layer thickness by evenly raking the notched trowel over adhesive layer. Install wood flooring during specified open time, slide in and press down firmly. Depending on the degree of setting, adhesive residues can be removed with the appropriate STAUF cleaners. Please test the effect of the cleaner on the finish of the wood flooring in an inconspicuous area or on a sample prior to applying the cleaner. Under the most unfavorable conditions or after a long setting time, hardened adhesive residues may only be removed mechanically, possibly damaging the surface of the flooring. It is therefore recommended to remove contaminations while still fresh or avoid contaminations from the start by organizing work sequences accordingly. After mixing, use adhesive during specified pot life.

Accessibility

Load bearing capacity depends on room climate.

Limitation of liability

The foregoing representations are based on the results of our most current product and material testing and are of a non-obligatory advisory nature only since we have no control over the actual quality of workmanship, materials used and worksite conditions. As such, they do not constitute an express or implied warranty of any kind. The same applies to our commercial and technical consultation services which are provided free-of-charge and without obligation. Therefore, we strongly recommend that prior on-site testing be conducted to observe and study the suitability of the product for the intended purpose. With the release of this technical information, all prior technical information (technical data sheets, installation recommendations and other information regarding similar purposes) becomes invalid.